Kotex Polycarbonate

型号: KG-30MRA 30% 玻纤加强 颜色: 原色、高粘性、易脱模

特性	温にサナンナ	测学长处	公 从	*/ ∔₽
行任	测定方法	测定标准	单位	数据
机械特性	<u> </u>			
Izod 冲击强度	ASTM D256	23°C V-notched 1/8"	J/m	100
			kgf•cm/cm	10
			ft·lbf/in	1.8
拉伸强度			MPa	127
	ASTM D638		kgf/cm²	1300
			lbf/in²	18500
断裂伸长度	ASTM D638		%	3
弯曲强度	ASTM D790		MPa	162
			kgf/cm²	1650
			lbf/in²	23400
弯曲模量			MPa	7550
	ASTM D790		kgf/cm²	77000
			lbf/in²	1090000
热特性				
熔体流动率	ASTM D1238	300°C, 1.2kgf	g/10min	
热变形温度	ASTM D648	18.6 kgf/cm²	°C	146
			°F	294
电力特性				
绝缘强度	ASTM D149	1.6mm	kV/mm	20
电容率	ASTM D150	10 ⁶ Hz		3.2
介电损耗因子	ASTM D150	10 ⁶ Hz		0.008
弧阻	ASTM D495		Sec.	110
体积电阻率	ASTM D257		Ω•cm	10 ¹⁶
光学特性				
透光系数	ASTM D1003	3 mm	%	
光折射率	ASTM D542			
模糊	ASTM D1003	3 mm	%	Translucent
物理特性				
比重	ASTM D792			1.43
吸水性	ASTM D570	24 小时 23℃浸水	%	≦ 0.2
模具收缩	ASTM D955		%	0.3~0.5
燃烧性	UL94			V-0 @ 3.0 mm

To our best knowledge, the values contained herein are typical of uncoloured PC and given in good faith. They may be affected by colorants, other additives, the design of a mould/die, moulding techniques applied, the size and shape of a moulded article. In view of these factors, the properties do not relieve customers from carrying out their own investigations and tests. It is entirely the customer's responsibility to determine the suitability of material and grade used for their intended application. No warranty, express or implied is made nor is liability accepted in connection with any of the information provided. We reserve the right to make additions, deletions, or modifications to the information at any time without prior notification. Kotec Corporation (30.3.2009)